

CAC304C(HBsC4C)

高力黄銅一般標準材

板 Flat

連铸品(Continuous castings)
押出品(Extrusions)比重(Specific gravity) $\rho=7.70$

High strength brass

材質規格(Material specification)

材質 Material	成分 Chemical composition	機械的性質 Mechanical properties			標準長さ Standard length mm
		引張強さ Tensile strength N/mm ²	伸び Elongation %	ブリネル硬度 Brinell hardness HBW 10/3000	
JIS CAC304C (HBsC4C)	Cu 60.0~65.0 Zn 22.0~28.0 Fe 2.0~4.0	765 min	14 min	参考規格 Reference (200 min)	連铸品(C.C)* 2030(+20/-30) 押出品(EX)** 1,230 1,430 (2,030)
JSP-1 (Brand)	Al 5.0~7.5 Mn 2.5~5.0	;	14 min	200 min	
JSP-5 (Brand)	Sn 0.2max,Pb 0.2max Ni 0.5max,Si 0.1max	785 min	12 min	240 min	
相当材 Nearest	ASTM C86300/USA, SAE430B/USA, HTB3/BS CuZn34Al5MnFe3(CC762S)/EN,DIN				

* C.C=Continuous castings

** EX=Extrusions

Code	製造法 Conditions	ブランド名 Brand name	呼称寸法 Nominal size	納入寸法(Delivery size)		単重 Unit wt. Kgs/m	備考 Remarks
			厚み x 幅 t x w	厚み Thickness (t)	幅 Width(w)		
1002	押出 (Ex)	JSP-5	10 x 28	11.5 +1.0/0	x 30.0 +1.0/0	2.82	
:	:	:	x 35	11.5 +1.0/0	x 37.0 +1.5/0	3.49	
:	:	:	x 38	11.5 +1.0/0	x 40.0 +1.5/0	3.77	
:	:	:	x 48	11.5 +1.0/0	x 50.0 +1.5/0	4.69	
:	:	:	x 50	11.5 +1.0/0	x 52.0 +1.5/0	4.87	
:	:	:	x 75	11.5 +1.0/0	x 77.0 +1.5/0	7.18	
:	:	:	x 100	11.5 +1.0/0	x 102.0 +1.5/0	9.49	
:	:	:	x 120	11.5 +1.0/0	x 122.0 +1.5/0	11.34	
:	:	:	12 x 50	13.5 +1.0/0	x 52.0 +1.5/0	5.69	
:	:	:	x 60	13.5 +1.0/0	x 62.0 +1.5/0	6.76	
:	:	:	x 80	13.5 +1.0/0	x 82.0 +1.5/0	8.92	
:	:	:	x 100	13.5 +1.0/0	x 102.0 +1.5/0	11.08	
:	:	:	x 120	13.5 +1.0/0	x 122.0 +1.5/0	13.23	
:	:	:	20 x 50	21.5 +1.0/0	x 52.0 +1.5/0	8.94	
:	:	:	x 75	21.5 +1.0/0	x 77.0 +1.5/0	13.17	
:	:	:	x 80	21.5 +1.0/0	x 82.0 +1.5/0	14.02	
:	:	:	x 100	21.5 +1.0/0	x 102.0 +1.5/0	17.41	
:	:	:	25 x 80	26.5 +1.0/0	x 82.0 +1.5/0	17.20	
:	:	:	x 100	26.5 +1.0/0	x 102.0 +1.5/0	21.36	
0840	連铸 (C. C)	JSP-1	20 x 125	24.0 ± 0.6	x 130.0 ±1.0	24.02	
:	:	:	x 150	24.0 ± 0.6	x 155.0 ±1.0	28.64	
:	:	:	x 160	24.0 ± 0.6	x 165.0 ±1.0	30.49	
:	:	:	25 x 150	29.0 ± 0.6	x 155.0 ±1.0	34.61	


比重(Specific gravity) $\rho = 7.70$

High strength brass

Code	製造法 Conditions	ブランド名 Brand name	呼称寸法 Nominal size		納入寸法(Delivery size)			単重 Unit wt. Kgs/m	備考 Remarks
			外径 O.D	内径 I.D	外径 O.D	x	内径 I.D		
1002	押出(Ex)	JSP-5	15	x -	16.0	(+1.0/0)	x -	1.65	
:	:	:	19	x -	20.0	(+1.0/0)	x -	2.54	
:	:	:	23	x -	24.0	(+1.0/0)	x -	3.63	
:	:	:	24	x -	25.0	(+1.0/0)	x -	3.93	
:	:	:	29	x -	30.0	(+1.0/0)	x -	5.62	
:	:	:	30	x -	31.0	(+1.0/0)	x -	6.00	
:	:	:		x 15	31.0	(+1.0/0)	x 13.0 (0/-1.0)	5.05	
:	:	:		x 20	31.0	(+1.0/0)	x 18.5 (0/-1.0)	4.04	
:	:	:	35	x -	36.0	(+1.0/0)	x -	8.05	
:	:	:		x 25	36.0	(+1.0/0)	x 23.5 (0/-1.0)	4.86	
:	:	:	40	x -	41.0	(+1.0/0)	x -	10.41	
:	:	:		x 20	41.0	(+1.0/0)	x 18.0 (0/-1.0)	8.56	
:	:	:		x 30	41.0	(+1.0/0)	x 28.5 (0/-1.0)	5.67	
:	:	:	45	x 25	46.0	(+1.0/0)	x 23.0 (0/-1.0)	10.01	
:	:	:		x 35	46.0	(+1.0/0)	x 33.5 (0/-1.0)	6.49	
:	:	:	50	x -	51.0	(+1.0/0)	x -	16.03	
:	:	:		x 30	51.0	(+1.0/0)	x 28.0 (0/-1.0)	11.46	
:	:	:		x 38	51.0	(+1.0/0)	x 36.5 (0/-1.0)	8.20	
:	:	:		x 40	51.0	(+1.0/0)	x 38.5 (0/-1.0)	7.30	
:	:	:	55	x 25	56.0	(+1.0/0)	x 22.5 (0/-1.0)	16.37	
:	:	:	56	x 35	57.0	(+1.0/0)	x 33.0 (0/-1.0)	13.60	
:	:	:		x 40	57.0	(+1.0/0)	x 38.5 (0/-1.0)	11.26	
:	:	:		x 45	57.0	(+1.0/0)	x 43.5 (0/-1.0)	8.81	
:	:	:	60	x 30	61.0	(+1.0/0)	x 27.5 (0/-1.0)	18.46	
:	:	:		x 35	61.0	(+1.0/0)	x 33.0 (0/-1.0)	16.48	
:	:	:		x 45	61.0	(+1.0/0)	x 43.5 (0/-1.0)	11.69	
:	:	:		x 48	61.0	(+1.0/0)	x 46.5 (0/-1.0)	10.07	
:	:	:	65	x 40	66.0	(+1.0/0)	x 38.0 (0/-1.0)	18.23	
:	:	:		x 50	66.0	(+1.0/0)	x 48.5 (0/-1.0)	12.80	
:	:	:		x 55	66.0	(+1.0/0)	x 53.5 (0/-1.0)	9.75	
:	:	:	70	x 35	71.0	(+1.0/0)	x 32.5 (0/-1.0)	24.71	
:	:	:		x 45	71.0	(+1.0/0)	x 43.0 (0/-1.0)	19.98	
:	:	:		x 55	71.0	(+1.0/0)	x 53.5 (0/-1.0)	13.92	
:	:	:		x 60	71.0	(+1.0/0)	x 58.5 (0/-1.0)	10.57	
:	:	:	75	x 50	76.5	(+1.2/0)	x 48.0 (0/-1.2)	22.35	
:	:	:		x 60	76.5	(+1.2/0)	x 58.0 (0/-1.2)	16.02	
:	:	:	80	x 65	81.5	(+1.2/0)	x 63.0 (0/-1.2)	17.21	
:	:	:	85	x 60	86.5	(+1.2/0)	x 58.0 (0/-1.2)	25.94	
:	:	:	85	x 70	86.5	(+1.2/0)	x 68.0 (0/-1.2)	18.40	
:	:	:	90	x 70	91.5	(+1.2/0)	x 68.0 (0/-1.2)	23.81	
:	:	:		x 75	91.5	(+1.2/0)	x 73.0 (0/-1.2)	19.59	
:	:	:	96	x 80	97.5	(+1.2/0)	x 78.0 (0/-1.2)	21.96	
:	:	:	100	x 80	102.0	(+1.5/0)	x 77.5 (0/-1.5)	28.21	
:	:	:		x 85	102.0	(+1.5/0)	x 82.5 (0/-1.5)	23.42	
:	:	:	102	x 85	104.0	(+1.5/0)	x 82.5 (0/-1.5)	25.93	
:	:	:	105	x 90	107.0	(+1.5/0)	x 87.5 (0/-1.5)	24.69	
:	:	:	110	x 80	112.0	(+1.5/0)	x 77.5 (0/-1.5)	41.24	
:	:	:		x 90	112.0	(+1.5/0)	x 87.5 (0/-1.5)	31.35	

CAC304C(HBsC4C)				高力黄銅一般標準材		丸棒・丸管 連鑄品 Continuous castings	
比重(Specific gravity) $\rho=7.70$				High strength brass			
Code	製造法 Conditions	ブランド名 Brand name	呼称寸法 Nominal size	納入寸法(Delivery size)		単重 Unit wt. Kgs/m	備考 Remarks
			外径 O.D	x 内径 I.D	外径 O.D		
0842	連鑄(C.C)	JSP-5	115 x 100	118.5 ± 0.8	x 95.5 ± 1.0	29.75	
:	:	:	120 x 100	123.5 ± 0.8	x 95.5 ± 1.0	37.06	
:	:	:	130 x 110	133.5 ± 0.8	x 105.5 ± 1.0	40.45	
:	:	:	140 x 120	144.0 ± 1.0	x 115.0 ± 1.3	45.40	
:	:	:	145 x 115	149.0 ± 1.0	x 110.0 ± 1.3	61.06	
:	:	:	x 130	149.0 ± 1.0	x 122.0 ± 1.0	44.23	
:	:	:	160 x 130	164.5 ± 1.3	x 124.5 ± 1.6	69.87	
0840	連鑄(C.C)	JSP-1	115 x 100	118.5 ± 0.8	x 95.5 ± 1.0	29.75	
:	:	:	120 x 100	123.5 ± 0.8	x 95.5 ± 1.0	37.06	
:	:	:	130 x 110	133.5 ± 0.8	x 105.5 ± 1.0	40.45	
:	:	:	145 x 130	149.0 ± 1.0	x 122.0 ± 1.0	44.23	
:	:	:	150 x 125	154.0 ± 1.0	x 120.5 ± 1.0	55.58	
:	:	:	180 x 150	185.0 ± 1.5	x 144.0 ± 1.8	81.53	
:	:	:	215 x 180	220.5 ± 1.7	x 173.5 ± 2.0	111.93	

直接押し複動型 Direct extrusion with double action type



参考資料

For information

硬さ換算表

(C2600黄銅(Cu70-Zn30) ASTMより抜粋)
Hardness conversion table from ASTM

ビッカース Vickers	ロックウェル Rockwell		ブリネル
	B Scale	F Scale	Brinell
	1000kgf-load		
	φ 1/16in ball		10mm ball
HV	HRB	HRF	HB
196	93.5	110.0	169
194	...	109.5	167
192	93.0	...	166
190	92.5	109.0	164
188	92.0	...	162
186	91.5	108.5	161
184	91.0	...	159
182	90.5	108.0	157
180	90.0	107.5	156
178	89.0	...	154
176	88.5	107.0	152
174	88.0	...	150
172	87.5	106.5	149
170	87.0	...	147
168	86.0	106.0	146
166	85.5	...	144
164	85.0	105.5	142
162	84.0	105.0	141
160	83.5	...	139
158	83.0	104.5	138
156	82.0	104.0	136
154	81.5	103.5	135
152	80.5	103.0	133
150	80.0	...	131
148	79.0	102.5	129
146	78.0	102.0	128
144	77.5	101.5	126
142	77.0	101.0	124
140	76.0	100.5	122
138	75.0	100.0	121
136	74.5	99.5	120
134	73.5	99.0	118
132	73.0	98.5	116
130	72.0	98.0	114
128	71.0	97.5	113
126	70.0	97.0	112
124	69.0	96.5	110
122	68.0	96.0	108
120	67.0	95.5	106
118	66.0	95.0	105
116	65.0	94.5	103
114	64.0	94.0	101
112	63.0	93.0	99
110	62.0	92.6	97
108	61.0	92.0	95
106	59.5	91.2	94
104	58.0	90.5	92
102	57.0	89.8	90
100	56.0	89.0	88
98	54.0	88.0	86
96	53.0	87.2	85

ビッカース Vickers	ロックウェル Rockwell		ブリネル Brinell
	B Scale	F Scale	
	1000kgf-load		
	φ 1/16in ball		
HV	HRB	HRF	HB
94	51.0	86.3	83
92	49.5	85.4	82
90	47.5	84.4	80
88	46.0	83.5	79
86	44.0	82.3	77
84	42.0	81.2	76
82	40.0	80.0	74
80	37.5	78.6	72
78	35.0	77.4	70
76	32.5	76.0	68
74	30.0	74.8	66
72	27.5	73.2	64
70	24.5	71.8	63
68	21.5	70.0	62
66	18.5	68.5	61
64	15.5	66.8	59
62	12.5	65.0	57
60	10.0	62.5	55
58		61.0	53
56		58.8	52
54		56.5	50
52		53.5	48
50		50.5	47
49		49.0	46
48		47.0	45
47		45.0	44
46		43.0	43
45		40.0	42